

1017121904
yrc 10/12/08

Aug. 8. 2007 2:51PM Owens Corning

RECEIVED
CENTRAL FAX CENTER

No. 9977 P. 7

AUG 08 2007

25090A

AMENDMENT TO THE SPECIFICATION

4 line 30 to page 5, line 13
At page 6, ~~lines 3-19~~, please amend the specification as follows:

yrc 11/12/08

The glass-melting furnace 10 preferably includes two molten glass zones, a generally upstream melting zone 26 and a generally downstream fining zone 28. The melting zone 26 is considered the upstream zone of the glass-melting furnace 10 wherein the glass-forming material 30 is charged into the glass-melting furnace 10 using a charger or charging device 32. The charging device 32 may be of any type suitable for depositing glass-forming material 30 into the glass-melting furnace 10. The glass forming material 30 may be a mixture of raw materials typically used in the manufacture of glass, such as for example glass batch. It will be appreciated that the glass-forming material 30 make-up is dependent on the type of glass product (not shown) being produced. Normally, the material includes silica-containing materials including finely ground scrap glass commonly referred to as cullet. Other glass-forming materials including feldspar, limestone, dolomite, soda ash, potash, borax and alumina may also be used. To alter the properties of the glass product, a relatively minor amount of arsenic, antimony, sulfates, carbon and/or fluorides may also be added. It will be appreciated that the molten glass 25 generally freely flows in an unimpeded manner from the upstream end 6 of the glass-melting furnace 10 to the downstream end 8 of the glass-melting furnace 10, as indicated by the arrows 27. It will also be noted that the elongated channel 11 contains no obstructions to impede such flow of the molten glass.

6 lines 3-15
At page 7, ~~line 16 to page 8, line 2~~, please amend the specification as follows:

yrc 11/12/08

After the glass-forming material is melted by the flames 36 and by heat radiated from other parts of the furnace, the molten glass freely flows in an unimpeded manner from the melting zone 26 in the direction of directional arrow 27 to the fining zone 28. It